

UNEXPECTED PURPOSE

Rewritten

| | |
|-------------------------|---|
| Construction | Tufted, Textured Loop Pile |
| Face Fibre | ECONYL® Solution Dyed 100% recycled Nylon 6 |
| Soil Release | StainSmart® for soil release, liquid repellence - selected colours only (see below)* |
| Finished Face Weight | 510 g/m ² |
| Gauge | 47.2 / 10 cm |
| Rows | 47.2 / 10 cm |
| Tuft Density | 222,047 /m ² |
| Finished Pile Height | 2.9 mm |
| Standard Backing | Comfort Lite 90% recycled open cell polyurethane cushion backing Available with TractionBack® on request |
| Nominal Total Thickness | 8.5 mm |
| Tile Size | 50 cm x 50 cm |
| Nominal Total Weight | 4100 g/m ² |
| Tiles per Box | 22 (5.5m ²) |

PERFORMANCE

| | |
|--|---|
| Flammability (Euroclassification EN13501:1-2018) | Class Bfl - s1 |
| Flammability (Radiant Panel ASTM-E-648) | Class 1 |
| Flammability (Hot Metal Nut BS4790) | Low Radius of Char |
| Use Classification (EN 1307) | Class 33 Heavy Commercial Use |
| Castor Chair (BS EN 985:2001) | Class A - Intensive use (r value ≥ 2.4) |
| Static Electricity (ISO 6356) | Pass ≤ 2.0 KV Permanent Conductive Fibre |
| Impact Sound (ISO 10140-3) | 28 dB |
| Sound Absorption (ISO354) | 0.25 (H) Class E |
| Alpha s values | 125Hz 0.00, 250Hz 0.05, 500Hz 0.30, 1000Hz 0.20, 2000Hz 0.25, 4000Hz 0.35 |

ENVIRONMENTAL

69% recycled content by total product weight

Manufactured in ISO14001 certified location using renewable sources

M/PACT Carbon Neutral Floors,
4.06 kg CO₂ e/m² Embodied Carbon (EPD calculation A1-A3)
Cradle to Gate footprint 100% off set

WARRANTIES

12 year wear warranty

Lifetime Antistatic guarantee

Latent Defects guarantee

***StainSmart® Applied to the following colours only**


Rendition - Authentic

CERTIFICATIONS

www.millikenfloors.com/gb/tech

| | | | | | | | | | | | | | |
|--|--|--|--|--|--|--|--|--|--|--|--|--|--|
| | | | | | | | | | | | | | |
| | | | | | | | | | | | | | |

INSTALLATION



Non-directional /
Batchless

CE / UKCA

| | | | | | | |
|--------------------------------------|--------------------------------------|--|--|--|--|--|
| | | | | | | |
| DOP-2895-1004-02 BS EN 14041:2018 | DOP-0338-1004-02 BS EN 14041:2018 | | | | | |