

THE TEXTURED POS&NEG

Light Reflectance Value (LRV) is the total quantity of visible and usable light that is reflected by a surface (e.g. flooring, walls, furniture,...) in all directions and at all wavelengths when illuminated by a light source.

LRV is a measurement that indicates how much light a surface reflects, and conversely how much it absorbs. LRV runs on a scale form 0% to 100% being a perfectly absorbing surface (black) up to 100% being a perfectly reflective surface (white). Additional to the colour of the surface, structure and gloss are factors that influence the light reflectance value.

The LRV certificates of all BLOQ products are tested by CRET which executes the measurement according to the EN 17327: 2020. BS 8493: 2008 Light Reflectance value (LRV) of a surface — Method of test.

POS	LRV _{av}	L
971	41.61	70.60
221	40.70	69.97
226	38.48	68.37
231	40.28	69.67
980	40.68	69.95
821	36.95	67.24
816	34.39	65.27
626	39.78	69.31

NEG	LRV _{av}	L
972	23.48	55.57
222	23.69	55.78
227	24.28	56.36
232	20.73	52.66
981	15.57	46.42
822	17.54	48.93
817	20.89	52.83
627	20.06	51.90